
Revision: 06.12.2018



Revision: 06.12.2018

Trade name: R102 NYLON BAG THINNER

| | (Contd. of page 1) | | | | | |
|------------------------------------|--|--|--|--|--|--|
| Precautionary sta | itements | | | | | |
| P210 | Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. | | | | | |
| | No smoking. | | | | | |
| P301+P310 | IF SWALLOWED: Immediately call a POISON CENTER/ doctor. | | | | | |
| P331 | Do NOT induce vomiting. | | | | | |
| P303+P361+P35 | 3 IF ON SKIN (or hair): Take off immediately all contaminated clothing. Rinse skin | | | | | |
| | with water/shower. | | | | | |
| P405 | Store locked up. | | | | | |
| P501 | Dispose of contents/container in accordance with local/regional/national/ | | | | | |
| | international regulations. | | | | | |
| 2.3 Other hazard | 5 | | | | | |
| Results of PBT and vPvB assessment | | | | | | |

· **PBT:** Not applicable.

· vPvB: Not applicable.

SECTION 3: Composition/information on ingredients

· 3.2 Chemical characterisation: Mixtures

· Description: Mixture of substances listed below with nonhazardous additions.

· Dangerous components.

| | Dangerous components. | | | |
|---|-----------------------|---|---------|--|
| | | | 50-100% | |
| j | EINECS: 265-198-5 | 🗞 Asp. Tox. 1, H304 | | |
| | | 1 ethoxy-2-propanol | 25-50% | |
| Ì | EINECS: 216-374-5 | 🚸 Flam. Liq. 3, H226; 🚸 STOT SE 3, H336 | | |
| • Additional information • For the wording of the listed hazard phrases refer to section 16 | | | | |

Additional information: For the wording of the listed hazard phrases refer to section 16.

SECTION 4: First aid measures

• 4.1 Description of first aid measures

- · After inhalation: Supply fresh air; consult doctor in case of complaints.
- After skin contact: Generally the product does not irritate the skin.
- · After eye contact:

Rinse opened eye for several minutes under running water. If symptoms persist, consult a doctor.

- After swallowing: If symptoms persist consult doctor.
- · 4.2 Most important symptoms and effects, both acute and delayed No further relevant information available.
- · 4.3 Indication of any immediate medical attention and special treatment needed No further relevant information available.

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- · Suitable extinguishing agents: CO2, sand, extinguishing powder. Do not use water.
- · For safety reasons unsuitable extinguishing agents: Water with full jet
- 5.2 Special hazards arising from the substance or mixture No further relevant information available.

(Contd. on page 3) GB

Revision: 06.12.2018

(Contd. of page 2)

Trade name: R102 NYLON BAG THINNER

· 5.3 Advice for firefighters

• Protective equipment: No special measures required.

SECTION 6: Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Wear protective equipment. Keep unprotected persons away.
- 6.2 Environmental precautions: Inform respective authorities in case of seepage into water course or sewage system. Do not allow to enter sewers/ surface or ground water.
- 6.3 Methods and material for containment and cleaning up: Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust). Dispose contaminated material as waste according to item 13. Ensure adequate ventilation. Do not flush with water or aqueous cleansing agents

• 6.4 Reference to other sections See Section 7 for information on safe handling. See Section 8 for information on personal protection equipment. See Section 13 for disposal information.

SECTION 7: Handling and storage

- 7.1 Precautions for safe handling Ensure good ventilation/exhaustion at the workplace. Prevent formation of aerosols.
- Information about fire and explosion protection: Keep ignition sources away - Do not smoke. Protect against electrostatic charges.
- · 7.2 Conditions for safe storage, including any incompatibilities
- · Storage:
- Requirements to be met by storerooms and receptacles: No special requirements.
- · Information about storage in one common storage facility: Not required.
- · Further information about storage conditions: Keep container tightly sealed.
- 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

· Additional information about design of technical facilities: No further data; see item 7.

· 8.1 Control parameters

• Ingredients with limit values that require monitoring at the workplace:

64742-94-5 Solvent naphtha (petroleum), heavy arom.

OEL Long-term value: 70 ppm

RECOMMENDED

• Additional information: The lists valid during the making were used as basis.

(Contd. on page 4)

Revision: 06.12.2018

Trade name: R102 NYLON BAG THINNER

(Contd. of page 3)

GB

| Avoid contact with the eyes and skin. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longe exposure use self-contained respiratory protective device. Protection of hands: The glow material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ th preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of severa substances, the resistance of the glove material can not be calculated in advance and has therefore to b checked prior to the application. Penetration time of glove material Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Eye protection: Section of busice physical and chemical properties General Information Appearance: Form: Fluid Colour: Characteristic Mot determined. PH-value: Not determined. | | (Contd. of page 3) | |
|--|---|--|--|
| Personal protective equipment: General protective and hygicatic measures: Keep away from foodsniffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Avoid contact with the eyes. Avoid contact with the eyes. Avoid contact with the eyes. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longe exposure use self-contained respiratory protective device. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Plastic gloves Plastic gloves Plastic gloves Plastic gloves resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Strong material gloves Rubber gloves Strong material gloves Strong material gloves Strong states of the gloggles Storng the selection of Difference in the splication chemical properties General Information Appearance: Form: Fuid Colour: Colour: Colour: Characteristic Odour threshold: Not determined. Pi-value: Not determined. | 8.2 Exposure controls | | |
| General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Avoid contact with the eyes. Avoid contact with the eyes. Avoid contact with the eyes. Avoid contact with the eyes. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of severa substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Eye protection: SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Fuid Colour: Characteristic Odour: Characteristic Mot determined. PI-value: Not determined. | | | |
| Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longe exposure use self-contained respiratory protective device. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of severa substances, the resistance of the glove material can not be calculated in advance and has therefore to b checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves SteCTION 9: Physical and chemical properties General Information Appearance: Form: Found: Found: Colour: Characteristic Odour: Characteristic Mot determined. PH-value: Not determined. | | | |
| Wash hands before breaks and at the end of work. Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longe exposure use self-contained respiratory protective device. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves made of the following materials: Leather gloves Step rotection: Step rotection: S | | | |
| Avoid contact with the eyes. Avoid contact with the eyes and skin. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longe exposure use self-contained respiratory protective device. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ th preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Pentration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Strong material gloves | | | |
| Avoid contact with the eyes and skin. Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longe exposure use self-contained respiratory protective device. Protection of hands: The glow material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ th preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of severa substances, the resistance of the glove material can not be calculated in advance and has therefore to b checked prior to the application. Penetration time of glove material Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Eye protection: Section of busice physical and chemical properties General Information Appearance: Form: Fluid Colour: Characteristic Mot determined. PH-value: Not determined. | Wash hands before breaks and a | at the end of work. | |
| Respiratory protection: In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longe exposure use self-contained respiratory protective device. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks or quality and varies from manufacturer to manufacturer. As the product is a preparation of severa substances, the resistance of the glove material Particip gloves Penetration time of glove material The selection time of glove material Preserved. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Eye protection: Tightly sealed goggles Strong material gloves Rubber gloves Eye protection: Strong material gloves Pormaterial longouse Pormation on basi | Avoid contact with the eyes. | | |
| In case of brief exposure or low pollution use respiratory filter device. In case of intensive or longe exposure use self-contained respiratory protective device. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks or quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has the beoserved. Not suitable gloves Strong material gloves Experiment of the following materials: Leather gloves Experiment Experiment Selection: Selection: Selection: Selection: Form: Form: Form: Form: Form: Fluid Colour: Co | Avoid contact with the eyes and | skin. | |
| exposure use self-contained respiratory protective device. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ th preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves Plastic gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks o quality and varies from manufacturer to manufacturer. As the product is a preparation of severa substances, the resistance of the glove material can not be calculated in advance and has therefore to b checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Eye protection: SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Form: Form: Form: Form: Fluid Colour: Characteristic Mot determined. Fluid: Not determined. Fluide: Not determined. Fluide: Colour threshold: Fluide: Colour threshold: Fluide: Colour threshold: Fluide: Form: Form: Fluide Fluide: Form: Fluide Fluide: Form: Fluide Fluide Fluide: Form: Fluid Fluide Fluide Fluide Fluide Fluide: Form: Fluid Fluide F | Respiratory protection: | | |
| Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of severa substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves Rubber gloves Strong material gloves Strong material gloves | In case of brief exposure or lo | w pollution use respiratory filter device. In case of intensive or longe | |
| The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Due to missing tests no recommendation to the glove material can be given for the product/ the preparation/ the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of severa substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Ruber gloves Strong material gloves Subtareial gloves Speparate Sect10N 9: Physical and chemical properties General Information <td< th=""><th>exposure use self-contained resp</th><th>piratory protective device.</th></td<> | exposure use self-contained resp | piratory protective device. | |
| Due to missing tests no recommendation to the glove material can be given for the product/th preparation/the chemical mixture. Selection of the glove material on consideration of the penetration times, rates of diffusion and th degradation Material of gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Eye protection: | Protection of hands: | | |
| Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of severa substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Eye protection: Tightly sealed goggles Secction: Secction: Secction: Secction: Tightly sealed goggles Secction: Secction: Secction: Secction: Secction: Secction: Secction: Second and chemical properties General Information Appearance: Form: Fluid Colour: According to product specific | Due to missing tests no recon | nmendation to the glove material can be given for the product/ the | |
| Material of gloves Plastic gloves Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of severa substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Eye protection: Viget ploves Strong material gloggels Strong material gloves Rubber gloves Strong material gloves Strong material gloggels Streperatics General Info | Selection of the glove material | | |
| Plastic gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Eye protection: Vot suitable and gloggles Strong material gloves Rubber gloves Eye protection: Vot Suitable and gloggles Strong material gloves Rubber gloves Eye protection: Vot suitable and gloggles Strong material gloves By and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined.< | Material of gloves | | |
| The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has the be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Eye protection: <i>o</i> Tightly sealed goggles <i>SECTION 9: Physical and chemical properties A</i> coording to product specification <i>A</i> coording to product specification <i>O</i> colour: <i>A</i> coording to product specification <i>O</i> dour threshold: <i>p</i> -value: | Plastic gloves | | |
| be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Eye protection: Tightly sealed goggles SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. pH-value: Not determined. | The selection of the suitable gloves does not only depend on the material, but also on furt quality and varies from manufacturer to manufacturer. As the product is a preparatio substances, the resistance of the glove material can not be calculated in advance and has th checked prior to the application. | | |
| be observed. Not suitable are gloves made of the following materials: Leather gloves Strong material gloves Rubber gloves Eye protection: Tightly sealed goggles SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. pH-value: Not determined. | | | |
| Leather gloves Strong material gloves Rubber gloves Eye protection: Tightly sealed goggles SECTION 9: Physical and chemical properties SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. pH-value: Not determined. | be observed. | | |
| Leather gloves Strong material gloves Rubber gloves Eye protection: Tightly sealed goggles SECTION 9: Physical and chemical properties SECTION 9: Physical and chemical properties General Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. pH-value: Not determined. | | | |
| Rubber gloves Eye protection: Tightly sealed goggles SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. pH-value: Not determined. | Leather gloves | | |
| Eye protection: Tightly sealed goggles SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. pH-value: Not determined. | Strong material gloves | | |
| Tightly sealed goggles SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. pH-value: Not determined. | Rubber gloves | | |
| SECTION 9: Physical and chemical properties 9.1 Information on basic physical and chemical properties General Information Appearance: Form: Fluid Colour: According to product specification Odour: Characteristic Odour threshold: Not determined. pH-value: Not determined. | Eye protection: | | |
| 9.1 Information on basic physical and chemical propertiesGeneral InformationAppearance:Form:FluidColour:According to product specificationOdour:CharacteristicOdour threshold:Not determined.pH-value:Not determined. | Tightly sealed goggle | 25 | |
| General InformationAppearance:Form:FluidColour:According to product specificationOdour:CharacteristicOdour threshold:Not determined.pH-value:Not determined. | SECTION 9: Physical and | l chemical properties | |
| Appearance:Form:FluidColour:According to product specificationOdour:CharacteristicOdour threshold:Not determined.pH-value:Not determined. | 9.1 Information on basic physical and chemical properties General Information | | |
| Form:FluidColour:According to product specificationOdour:CharacteristicOdour threshold:Not determined.pH-value:Not determined. | General Information | | |
| Odour: Characteristic Odour threshold: Not determined. pH-value: Not determined. | | | |
| Odour:CharacteristicOdour threshold:Not determined.pH-value:Not determined. | Appearance: | Fluid | |
| pH-value: Not determined. | Appearance: Form: | | |
| • | Appearance: Form: | According to product specification | |
| • | Appearance: Form: Colour: Odour: | According to product specification Characteristic | |
| (Contd. on page 5 | Appearance: Form: Colour: Odour: Odour threshold: | According to product specification Characteristic Not determined. | |

Revision: 06.12.2018

Trade name: R102 NYLON BAG THINNER

| | (Contd. of page - |
|---|---|
| · Change in condition | |
| Melting point/freezing point: | Undetermined. |
| Initial boiling point and boiling range | : Undetermined. |
| · Flash point: | 45 °C |
| · Ignition temperature: | 255.0 °C |
| · Decomposition temperature: | Not determined. |
| • Auto-ignition temperature: | Product is not selfigniting. |
| · Explosive properties: | Product is not explosive. However, formation of explosive air vapour mixtures are possible. |
| · Explosion limits: | |
| Lower: | 1.3 Vol % |
| Upper: | 12.0 Vol % |
| · Vapour pressure at 20 °C: | 10.0 hPa |
| · Density at 20 °C: | 0.88 g/cm ³ |
| · Relative density | Not determined. |
| · Vapour density | Not determined. |
| · Evaporation rate | Not determined. |
| · Solubility in / Miscibility with | |
| water: | Not miscible or difficult to mix. |
| · Partition coefficient: n-octanol/water: | Not determined. |
| · Viscosity: | |
| Dynamic: | Not determined. |
| Kinematic: | Not determined. |
| · Solvent content: | |
| Organic solvents: | 33.3 % |
| VOC (EC) | 100.00 % |
| Solids content: | 66.7 % |
| • 9.2 Other information | No further relevant information available. |

SECTION 10: Stability and reactivity

- · 10.1 Reactivity No further relevant information available.
- · 10.2 Chemical stability
- · Thermal decomposition / conditions to be avoided:
- No decomposition if used according to specifications.
- 10.3 Possibility of hazardous reactions No dangerous reactions known.
- \cdot 10.4 Conditions to avoid No further relevant information available.
- \cdot 10.5 Incompatible materials: No further relevant information available.
- 10.6 Hazardous decomposition products: No dangerous decomposition products known.

(Contd. on page 6)

Revision: 06.12.2018

Trade name: R102 NYLON BAG THINNER

(Contd. of page 5)

SECTION 11: Toxicological information

· 11.1 Information on toxicological effects

• Acute toxicity Based on available data, the classification criteria are not met.

· Primary irritant effect:

· Skin corrosion/irritation Based on available data, the classification criteria are not met.

· Serious eye damage/irritation Based on available data, the classification criteria are not met.

- · Respiratory or skin sensitisation Based on available data, the classification criteria are not met.
- · CMR effects (carcinogenity, mutagenicity and toxicity for reproduction)

· Germ cell mutagenicity Based on available data, the classification criteria are not met.

· Carcinogenicity Based on available data, the classification criteria are not met.

• *Reproductive toxicity Based on available data, the classification criteria are not met.*

· STOT-single exposure

May cause drowsiness or dizziness.

· STOT-repeated exposure Based on available data, the classification criteria are not met.

· Aspiration hazard

May be fatal if swallowed and enters airways.

SECTION 12: Ecological information

- · 12.1 Toxicity
- · Aquatic toxicity: No further relevant information available.
- · 12.2 Persistence and degradability No further relevant information available.
- 12.3 Bioaccumulative potential No further relevant information available.
- · 12.4 Mobility in soil No further relevant information available.
- · Ecotoxical effects:
- Remark: Toxic for fish
- Additional ecological information:
- · General notes:

Water hazard class 2 (German Regulation) (Self-assessment): hazardous for water Do not allow product to reach ground water, water course or sewage system. Danger to drinking water if even small quantities leak into the ground.

Also poisonous for fish and plankton in water bodies.

- Toxic for aquatic organisms
- · 12.5 Results of PBT and vPvB assessment
- **PBT:** Not applicable.
- **vPvB:** Not applicable.
- · 12.6 Other adverse effects No further relevant information available.

SECTION 13: Disposal considerations

- · 13.1 Waste treatment methods
- · Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

(Contd. on page 7)

Revision: 06.12.2018

Trade name: R102 NYLON BAG THINNER

(Contd. of page 6)

Uncleaned packaging:
Recommendation: Disposal must be made according to official regulations.

| 14.1 UN-Number ADR, IMDG, IATA | 1263 |
|--|---|
| 14.2 UN proper shipping name ADR IMDG, IATA | 1263 PAINT RELATED MATERIAL PAINT RELATED MATERIAL |
| 14.3 Transport hazard class(es) | |
| ADR | |
| Class | 3 Flammable liquids. |
| IMDG | |
| Class | 3 Flammable liquids. |
| Label | 3 |
| IATA Class Label | 3 Flammable liquids. 3 |
| 14.4 Packing group IMDG, IATA | III |
| 14.5 Environmental hazards: | |
| Marine pollutant: | No Symbol (fish and tree) |
| Special marking (ADR): | Symbol (fish and tree) Symbol (fish and tree) |
| 14.6 Special precautions for user | Warning: Flammable liquids. |
| 14.7 Transport in bulk according to Ann Marpol and the IBC Code | ex II of Not applicable. |

Revision: 06.12.2018

Trade name: R102 NYLON BAG THINNER

(Contd. of page 7)

· UN ''Model Regulation'':

UN1263, PAINT RELATED MATERIAL, 3

SECTION 15: Regulatory information

- · 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture · Labelling according to Regulation (EC) No 1272/2008
- The product is classified and labelled according to the CLP regulation.
- Hazard pictograms GHS02, GHS07, GHS08
- · Signal word Danger
- Hazard-determining components of labelling: Solvent naphtha (petroleum), heavy arom. 1 ethoxy-2-propanol

• **Hazard statements** H226 Flammable liquid and vapour.

H336 May cause drowsiness or dizziness.

H304 May be fatal if swallowed and enters airways.

· Precautionary statements

P210 Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.

- P301+P310 IF SWALLOWED: Immediately call a POISON CENTER/ doctor.
- *P331 Do NOT induce vomiting.*

P303+P361+P353 IF ON SKIN (or hair): Take off immediately all contaminated clothing. Rinse skin with water/shower.
 P405 Store locked up.

P501 Dispose of contents/container in accordance with local/regional/national/ international regulations.

• REGULATION (EC) No 1907/2006 ANNEX XVII Conditions of restriction: 3

• 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

· Relevant phrases

H226 Flammable liquid and vapour. H304 May be fatal if swallowed and enters airways. H336 May cause drowsiness or dizziness.

- · Department issuing SDS: product safety department
- · Contact: Mr L.Cooper

· Abbreviations and acronyms:

RID: Règlement international concernant le transport des marchandises dangereuses par chemin de fer (Regulations Concerning the International Transport of Dangerous Goods by Rail) IATA-DGR: Dangerous Goods Regulations by the "International Air Transport Association" (IATA) ICAO: International Civil Aviation Organisation ICAO-TI: Technical Instructions by the "International Civil Aviation Organisation" (ICAO)

ADR: Accord européen sur le transport des marchandises dangereuses par Route (European Agreement concerning the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods

IATA: International Air Transport Association

(Contd. on page 9)

⁻ GB

Revision: 06.12.2018

Trade name: R102 NYLON BAG THINNER

| | (Contd. of page 8) |
|--|--------------------|
| GHS: Globally Harmonised System of Classification and Labelling of Chemicals | |
| EINECS: European Inventory of Existing Commercial Chemical Substances | |
| ELINCS: European List of Notified Chemical Substances | |
| CAS: Chemical Abstracts Service (division of the American Chemical Society) | |
| VOC: Volatile Organic Compounds (USA, EU) | |
| PBT: Persistent, Bioaccumulative and Toxic | |
| vPvB: very Persistent and very Bioaccumulative | |
| Flam. Liq. 3: Flammable liquids – Category 3 | |
| STOT SE 3: Specific target organ toxicity (single exposure) – Category 3 | |
| Asp. Tox. 1: Aspiration hazard – Category 1 | |
| | CB |